

## CBGEL

THERMAL LAMINATION FILM WITH GLOSS SURFACE - BOPP BASED



Adhesive Layer  
BOPP Film

16.6,  
18.43, 20.31,  
21.25, 21.25  
g/m<sup>2</sup>

AVAILABLE  
GRAMMAGE

### DESCRIPTION

A film with a glossy, shiny surface and excellent optics. It is bi-axially oriented polypropylene film with uniformly extrusion coated with adhesive all along the film surface.

### PRODUCT FEATURES

- Excellent optical properties
- It shows excellent bonding with all kinds of printed paper products.

### APPLICATIONS

- Paper boards, post card, photo books, textbooks, etc.

	PROPERTIES	POSITION	CBG18EL	CBG20EL	CBG22EL	CBG24EL	CBG25EL	UNIT	METHOD
GENERAL	Grammage	-	16.6	18.43	20.31	21.25	21.25	g/m <sup>2</sup>	ASTM D 1505
	Yield	-	60.24	54.26	49.24	47.06	47.06	m <sup>2</sup> /kg	Internal
SURFACE	Wetting tension	EVA side	44-46					dy/cm	ASTM D 2578
THERMAL	Lamination Temp.	-	90-100					°C	Internal

The above figures and properties refer to average values of laboratory test on samples of our standard production, it is understood that this entails no obligation or responsibility on our part. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a (end) product specification.

### SPECIAL INSTRUCTIONS

- Film to be laminated on above said lamination temperatures, however parameters can be optimized based on lamination speed / dwell time and/or dimensional stability.
- Printed surface must be well dried before lamination.
- In case of both side lamination, it is advised to cool one surface sufficiently before laminating the other surface.
- Surface printing is guaranteed only in specific products, all products are not meant for surface printing. Please contact MAX Technical Services representative prior to printing process.
- Temperature should preferably be less than 30°C & humidity 55±5% in storage areas.
- Material should be consumed within six months of receipt.
- Material should be kept in their original wrapping until the material is loaded on machine.
- Storage atmosphere should be dust free to avoid any contamination while lamination.

### SAFETY

Compliance with industrial health and safety standards. Max Thermal films do not present any significant danger to health and safety in the workplace provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed.