


## CST32EH

THERMAL LAMINATION FILM WITH SUPER SILK TOUCH - MATT BOPP BASED



Super Silk Touch  
BOPP Film  
EVA Layer

30.7  
g/m<sup>2</sup>

AVAILABLE  
GRAMMAGE

### DESCRIPTION

CST32EH is BOPP based product with luxurious super silk feel suitable for thermal lamination applications. The characteristics of super silk feel is achieved by proprietary chemical coating on the top surface as well as extrusion coated on opposite surface using special low melting adhesive for best encouragement with printed media.

### PRODUCT FEATURES

- Exceptional super silk touch for premium applications
- Excellent adhesion with printed media

### APPLICATIONS

- Book covers, Visiting cards, Invitation cards, liquor cartons, cosmetic boxes, Diaries, Shopping bags etc.
- Recommended for the application, where unique fluffy touch and luxurious finish is required.

### SURFACE PRINTABILITY OPTIONS

- Spot UV
- Foil Stampable

	PROPERTIES	POSITION	CST32EH	UNIT	METHOD
GENERAL	Grammage	-	30.7	g/m <sup>2</sup>	ASTM D 1505
	Yield	-	32.57	m <sup>2</sup> /kg	Internal
SURFACE	Wetting tension	Ex-coating side	44-46	dy/cm	ASTM D 2578
		Super Silk Side	42-44		
THERMAL	Lamination Temp.	-	90-110	°C	Internal

The above figures and properties refer to average values of laboratory test on samples of our standard production, it is understood that this entails no obligation or responsibility on our part. Customers should verify the suitability of the film for its specific end use. Therefore this document will not represent a (end) product specification.

**SPECIAL INSTRUCTIONS**

- Film to be laminated on above said lamination temperatures, however parameters can be optimized based on lamination speed / dwell time and/or dimensional stability.
- Printed surface must be well dried before lamination.
- In case of both side lamination, it is advised to cool one surface sufficiently before laminating the other surface.
- Surface printing is guaranteed only in specific products, all products are not meant for surface printing. Please contact MAX Technical Services representative prior to printing process.
- Temperature should preferably be less than 30°C & humidity 55±5% in storage areas.
- Material should be consumed within six months of receipt.
- Material should be kept in their original wrapping until the material is loaded on machine.
- Storage atmosphere should be dust free to avoid any contamination while lamination.

**SAFETY**

Compliance with industrial health and safety standards. Max Thermal films do not present any significant danger to health and safety in the workplace provided they are used for the intended purpose in accordance with conventional practices and that health & safety regulations are observed.